



DRILL PIPE SPECIFICATION DATA

5-1/2" 21.9# S-135 DRILL PIPE W/ CET54 CONNECTIONS

Pipe Body O.D.	(in)	5.500
Nominal Pipe I.D.	(in)	4.778
Nominal Weight Designation		21.90
Drill Pipe Adjusted Weight	(lbs./ft.)	24.25
Pipe Body Grade		S-135
Pipe Body Wall Thickness	(in)	0.361
API Class - Tube		Premium
Pipe Body Tensile	(lbs.)	629,447
Pipe Body Torsional	(ft./ lbs.)	73,023
Pipe Body Collapse	(psi)	10,139
Pipe Body Internal Yield / Burst	(psi)	12,406
Pipe Body Displacement	(gal/ft.)	0.3710
Pipe Body Capacity	(gal/ft.)	0.9120
Connection Type		CET54
Connection O.D.	(in)	6.625
Connection I.D.	(in)	4.000
Tool Joint Drift	(in)	3.875
Recommended Make Up Torque	(ft./ lbs.)	52,600
Minimum Make Up Torque	(ft./ lbs.)	44,800
Tool Joint Torsional Strength	(ft./ lbs.)	80,900
Tool Joint Tensile Strength (At Rec. MU)	(lbs.)	1,236,400

The technical information contained herein, including the product performance/spec sheets and other attached documents, have been generated from material provided by the manufacturer. It is for reference only and should not be construed as a recommendation. The user is fully responsible for the accuracy and suitability of use of all technical information. Platinum Pipe Rentals, LLC cannot assume responsibility for the results obtained through the use of this material. No expressed or implied warranty is intended. Assembly properties are based on uniform OD and wall thickness. No safety factor is applied. The information provided for various wear conditions (remaining body wall) is for information only and does not represent or imply acceptable operating limits. It is the responsibility of the customer and/or end user to determine the appropriate performance ratings, acceptable use of the product, maintain safe operational practices, and to apply a prudent safety factor suitable for the application. The user should consider all field conditions along with combined factors which may affect the final string design used in the field. Per the IADC drilling manual, it is recommended that drilling torque should not exceed 80% of MUT.